



Jacobson van den Berg (Hong Kong) Ltd.

8/F, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408



防火 V-0 及 15%玻璃纖維級 FLAME RETARDANT V-0 & 15% GLASS FIBER GRADE PBT 1184GA15

性能 Properties	ASTM 測驗方法 ASTM Standards	測試條件 Conditions	單位 Units	1184GA15
物理性能 Physical Properties				
填充成份 Filler Content	-	-	%	15
比重 Specific Gravity	D792	-	-	1.54
收縮率 Molding Shrinkage	-	80 x 80 x 3 plate	%	0.5—1.1
熱性能 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	D648	1.82MPa	°C	205
燃燒性 Flammability	UL-94	-	-	V-0 (0.75mm)
機械性能 Mechanical Properties				
拉伸強度 Tensile Strength	D638	23°C	MPa	110
拉伸長度 Tensile Elongation	D638	23°C, at break	%	3.8
撓曲強度 Flexural Strength	D790	23°C	MPa	150
彎曲模量 Flexural Modulus	D790	23°C	Gpa	5.7
艾佐德衝擊值 Izod Impact Strength	D256	Notched	J/m	60

上列數據僅供參考，並不為此承擔任何責任和保證。