



Jacobson van den Berg (Hong Kong) Ltd.

8/F, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408



防火 V-0/5VA 級 FLAME RESISTANT V-0/5VA GRADE PC EMERGE 4800-7

性能 Properties		測驗方法 Test Standards	測試條件 Conditions	單位 Units	EMERGE 4800-7
物理性能 Physical Properties					
比重 Specific Gravity		ASTM D792	—	g/cm ³	1.2
熔融流動率 Melt Flow Index		ASTM D1238	300°C / 1.2kg	g/10min	7
成形收縮率 Molding Shrinkage		ASTM D955	mm/mm	%	0.005 — 0.007
軟化溫度 Vicat Softening Temperature		ASTMD 1525	50°C/Hr	°C	151
洛氏硬度 Rockwell Hardness		ASTM D785	R scale	—	123
燃燒性 Flammability		—	UL-94	—	V-0 (1.5mm) V-0/5VA (3.0mm)
機械性能 Mechanical Properties					
拉伸模量 Tensile Modulus		ASSTM D638	—	MPa	2,380
屈服拉伸率 Elongation		ASTM D638	Break	%	115
抗拉強度 Tensile Strength		ASTM D638	Yield	MPa	61
			Break		59
撓曲強度 Flexural Strength		ASTM D790	—	MPa	98
彎曲模量 Flexural Modulus		ASTM D790	—	MPa	2,330
Izod 衝擊強度 Izod Impact Strength	Unnotched	ASTM D256	23°C	J/m	NB
Izod 衝擊強度 Izod Impact Strength	Notched	ASTM D256	23°C	J/m	800

上列數據仕僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.