



雅各臣(香港)有限公司

(Subsidiary of Chinney Alliance Group Ltd.)



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong

香港九龍青山道481-483號

Tel : (852) 2828 9328

香港紗廠工業大廈第六期8樓

Fax: (852) 2828 9408



A. Schulman

ALCRYN 2000 系列 MELT-PROCESSIBLE RUBBER ALCRYN® 2060 NC

性能 Properties		測驗方法 Test Method	單位 Units	ALCRYN® 2060 NC
機械性能 Mechanical Properties				
比重 Specific Gravity		ASTM D-471	—	1.12
硬度 Hardness		ASTM D-2240	Shore A	59
熱性能 Thermal Properties				
100% 模量 100% Modulus		—	psi	440
抗拉強度 Tensile Strength		—	psi	1,150
延伸率 Elongation	At break	—	%	420
撕裂模量 Torsion Modulus	At 75°F (24°C)	ASTM D1043	psi	340
	At -4°F (-20°C)			700
回彈性 Compression Set	After 22hr at 24°C	ASTM D395	%	13
	After 22hr at 100°C			62
耐熱性特質 Tensile Properties After 7 Days At 125°C				
100% 模量 100% Modulus		ASTM D573	psi	400
抗拉強度 Tensile Strength		ASTM D573	psi	950
延伸率 Elongation	At break	ASTM D573	%	340
硬度 Hardness		ASTM D573	Shore A	60
使用溫度 Service Temperature		—	°C	-40 — 107
低溫下特點 Low Temperature Properties				
脆點 Brittleness Temperature		—	°C	-85

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.