



雅各臣(香港)有限公司

(Subsidiary of Chinney Alliance Group Ltd.)



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong

香港九龍青山道481-483號

Tel : (852) 2828 9328

香港紗廠工業大廈第六期8樓

Fax: (852) 2828 9408



A. Schulman

ALCRYN 2000 系列 MELT-PROCESSIBLE RUBBER ALCRYN® 2080 NC

性能 Properties		測驗方法 Test Method	單位 Units	ALCRYN® 2080 NC
機械性能 Mechanical Properties				
比重 Specific Gravity		ASTM D-471	—	1.26
硬度 Hardness		ASTM D-2240	Shore A	76
熱性能 Thermal Properties				
100% 模量 100% Modulus		—	psi	770
抗拉強度 Tensile Strength		—	psi	1,440
延伸率 Elongation	At break	—	%	400
撕裂模量 Torsion Modulus	At 75°F (24°C)	ASTM D1043	psi	430
	At -4°F (-20°C)			2,080
回彈性 Compression Set	After 22hr at 24°C	ASTM D395	%	17
	After 22hr at 100°C			61
耐熱性特質 Tensile Properties After 7 Days At 125°C				
100% 模量 100% Modulus		ASTM D573	psi	640
抗拉強度 Tensile Strength		ASTM D573	psi	800
延伸率 Elongation	At break	ASTM D573	%	135
硬度 Hardness		ASTM D573	Shore A	71
使用溫度 Service Temperature		—	°C	-40 — 107
低溫下特點 Low Temperature Properties				
脆點 Brittleness Temperature		—	°C	-76

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.