



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408



防火 V-0 級 FLAME RESISTANT V-0 GRADE PP LUPOL GP-1000FC

性能 Properties		測驗方法 Test Method	單位 Units	LUPOL GP-1000FC
物理性質 Physical Properties				
比重 Specific Gravity		ASTM D792	—	1.0
熔融流動率 Melt Flow Index		ASTM D1238	g/10min	12
成型收縮率 Mold Shrinkage		ASTM D955	%	1.6 — 1.8
燃燒率 Flammability		UL-94	—	V-0 (0.75mm)
機械性能 Mechanical Properties				
抗拉強度 Tensile Strength		ASTM D638	kg/cm ²	350
延伸率 Tensile Elongation	At break	ASTM D638	%	70
彎曲強度 Flexural Strength		ASTM D790	kg/cm ²	510
彎曲模量 Flexural Modulus		ASTM D790	kg/cm ²	18,500
IZOD 衝擊強度 IZOD Impact Strength		ASTM D256	kg-cm/cm	6.0
熱性質 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	4.6kg	ASTM D648	℃	130

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.