



雅各臣(香港)有限公司

(Subsidiary of Chinney Alliance Group Ltd.)



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong

香港九龍青山道481-483號

Tel : (852) 2828 9328

香港紗廠工業大廈第六期8樓

Fax: (852) 2828 9408



吹塑及防火 V-2 級 BOLW MOLDING & FLAME RESISTANT V-2 GRADE PP LUPOL GP-1007FH

性能 Properties		測驗方法 Test Method	單位 Units	LUPOL GP-1007FH
物理性質 Physical Properties				
比重 Specific Gravity		ASTM D792	—	0.94
熔融流動率 Melt Flow Index		ASTM D1238	g/10min	2.4
成型收縮率 Mold Shrinkage		ASTM D955	%	1.6 — 1.8
燃燒率 Flammability		UL-94	—	V-2 (1.5mm)
機械性能 Mechanical Properties				
抗拉強度 Tensile Strength		ASTM D638	kg/cm ²	260
延伸率 Tensile Elongation	At break	ASTM D638	%	600
彎曲強度 Flexural Strength		ASTM D790	kg/cm ²	345
彎曲模量 Flexural Modulus		ASTM D790	kg/cm ²	12,500
IZOD 衝擊強度 IZOD Impact Strength		ASTM D256	kg-cm/cm	No Break
熱性質 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	4.6kg	ASTM D648	°C	120

上列數據仕僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.