



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408



防火 V-0 及 10%玻璃纖維級 FLAME RETARDANT V-0 & 10% GLASS FIBER GRADE ABS LUPOS GP-2106F

性能 Properties		測驗方法 Test Method	單位 Units	LUPOS GP-2106F
物理性質 Physical Properties				
比重 Specific Gravity		ASTM D792	—	1.25
成型收縮率 Mould Shrinkage		ASTM D955	%	0.1 – 0.3
燃燒率 Flammability		UL-94	—	V-0 (1.5mm)
機械性能 Mechanical Properties				
抗拉強度 Tensile Strength	At yield	ASTM D638	kg/cm ²	600
彎曲強度 Flexural Strength		ASTM D790	kg/cm ²	1,000
彎曲模量 Flexural Modulus		ASTM D790	kg/cm ²	45,000
延伸率 Tensile Elongation	At break	ASTM D638	%	7
IZOD 衝擊強度 IZOD Impact Strength	Notched, 23℃	ASTM D256	ft-lb/in	1.3
			kg-cm/cm	7.0
熱性質 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	1.82MPa	ASTM D648	℃	96
	0.45MPa			205

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.