



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408



30%玻璃纖維級 30% GLASS FIBER GRADE PP LUPOL® GP-2300

性能 Properties		測驗方法 Test Method	單位 Units	LUPOL® GP-2300
物理性質 Physical Properties				
比重 Specific Gravity		ASTM D792	-	1.15
成型收縮率 Mould Shrinkage		ASTM D955	%	0.3 – 0.5
燃燒率 Flammability		UL-94	-	HB (1.5mm)
機械性能 Mechanical Properties				
抗拉強度 Tensile Strength	At yield	ASTM D638	kg/cm ²	800
彎曲強度 Flexural Strength		ASTM D790	kg/cm ²	1,200
彎曲模量 Flexural Modulus		ASTM D790	kg/cm ²	50,000
延伸率 Tensile Elongation	At break	ASTM D638	%	8
IZOD 衝擊強度 IZOD Impact Strength	Notched, 23°C	ASTM D256	ft-lb/in kg-cm/cm	1.5 8
熱性質 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	1.82MPa	ASTM D648	°C	157

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.