



雅各臣(香港)有限公司

(Subsidiary of Chinney Alliance Group Ltd.)



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong

香港九龍青山道481-483號

Tel : (852) 2828 9328

香港紗廠工業大廈第六期8樓

Fax: (852) 2828 9408



防火 V-0 級 FLAME RESISTANT V-0 PC/ABS LUPOY GP-5008BF

性能 Properties		測驗方法 Test Method	單位 Units	LUPOY GP-5008BF
物理性質 Physical Properties				
比重 Specific Gravity		ASTM D792	-	1.20
成型收縮率 Mold Shrinkage		ASTM D955	%	0.5 –0.8
熔融流動率 Melt Flow Index		—	250℃, 2.16kgf	6
燃燒率 Flammability		UL-94	-	V-0 (1.5mm)
機械性能 Mechanical Properties				
抗拉強度 Tensile Strength		ASTM D638	kg/cm ²	580
			MPa	57
延伸率 Tensile Elongation		ASTM D638	%	50
彎曲強度 Flexural Strength		ASTM D790	kg/cm ²	840
			MPa	82
彎曲模量 Flexural Modulus		ASTM D790	kg/cm ²	24,000
			MPa	2,350
IZOD 衝擊強度 IZOD Impact Strength		ASTM D256	kg-cm/cm	60
			J/m	588
硬度 Hardness		ASTM D785	R	113
熱性質 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	1.82MPa	ASTM D648	℃	112

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.