



雅各臣(香港)有限公司

(Subsidiary of Chinney Alliance Group Ltd.)



Jacobson van den Berg (Hong Kong) Ltd.

8/F, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong

香港九龍青山道481-483號

Tel : (852) 2828 9328

香港紗廠工業大廈第六期8樓

Fax: (852) 2828 9408



尼龍 6T – 40%玻璃纖維、耐熱級 PA-6T – 40% GLASS FIBER & HIGH HEAT GRADE NYLON GRIVORY HT1V-4FWA

性能 Properties	測驗方法 Test Method	測試條件 Conditions		單位 Units	GRIVORY HT1V-4FWA
物理性能 Physical Properties					
填充成份 Filler Content	-	-		%	40
比重 Density	ISO 1183	dry 乾燥時		g/cm ³	1.53
吸水率 Water Absorption	ISO 62	23°C/sat.		%	3.5
濕水率 Moisture Absorption	ISO 62	23°C/50% r.h.		%	1.5
成形收縮率 Linear Molding Shrinkage	ISO 294 / EMS	long. / trans.	dry 乾燥時	%	0.1 / 0.6
熱性能 Thermal Properties					
融點 Melting Point	ISO 11357	DSC	dry 乾燥時	°C	325
熱變形溫度 Heat Deflection Temperature	ISO 75	HDT/A (1.80 MPa)	dry 乾燥時	°C	280
		HDT/C (8.00 MPa)			175
最高使用溫度 Maximal Usage Temperature	EMS	long term / short term	dry 乾燥時	°C	140 / 270
燃燒性 Flammability	UL 94	-		rating	HB (0.75mm)
機械性能 Mechanical Properties					
拉伸強度 Tensile Stress (Break)	ISO 527	yield / break 50 mm/min	dry 乾燥時	MPa	¹⁾ / 220
			cond. 吸濕後		¹⁾ / 210
斷裂伸長率 Tensile Strain (Break)	ISO 527	yield / break 50 mm/min	dry 乾燥時	%	¹⁾ / 2
			cond. 吸濕後		¹⁾ / 2
拉伸模量 Tensile Modulus	ISO 527	1 mm/min	dry 乾燥時	MPa	14,500
			cond. 吸濕後		14,000
Charpy 衝擊強度 Charpy Impact Strength	ISO 179/1eU	23°C	dry 乾燥時	kJ/m ²	70
			cond. 吸濕後		70
	ISO 179/1eA	23°C (notched)	dry 乾燥時		8
			cond. 吸濕後		8
電性能 Electrical Properties					
耐電壓 Dielectric Strength	IEC 243-1	K20 / P50	dry 乾燥時	kV/mm	35
			cond. 吸濕後		35
比較痕跡指數 Comparative Tracking Index	IEC 112	CTI	dry 乾燥時	-	-
			cond. 吸濕後		600
表面電阻系數 Specific Surface Resistivity	IEC 93	dry 乾燥時		Ω	-
		cond. 吸濕後			10 ¹²
體積電阻系數 Volume Resistivity	IEC 93	dry 乾燥時		Ω.cm	10 ¹³
		cond. 吸濕後			10 ¹³

1) Glass transition temperature

The test values <conditioned> were attained on test pieces stored according to ISO 1110.

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.