



雅各臣(香港)有限公司

(Subsidiary of Chinney Alliance Group Ltd.)



Jacobson van den Berg (Hong Kong) Ltd.

8/F, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong

香港九龍青山道481-483號

Tel : (852) 2828 9328

香港紗廠工業大廈第六期8樓

Fax: (852) 2828 9408



PCTG SKYGREEN JN200

性能 Properties		ASTM 測驗方法 ASTM Standards	單位 Units	SKYGREEN JN200
物理性能 Physical Properties				
比重 Specific Gravity		D792	—	1.23
熱性能 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	0.455 MPa (66 psi)	D648	°C	74
			°F	165
霧度 Haze		D1003	%	< 1.0
透光率 Total Light Transmittance		D1003	%	90
機械性能 Mechanical Properties				
拉伸強度 Tensile Strength	Yield	D638	MPa / (kgf/cm ²)	44 / (450)
	Break			53 / (540)
拉伸長度 Tensile Elongation At break		D638	%	340
撓曲強度 Flexural Strength		D790	MPa	67
			kgf/cm ²	685
彎曲模量 Flexural Modulus		D790	MPa	1,800
			kgf/cm ²	18,400
艾佐德衝擊值 Izod Impact Strength (23°C)		D256	J/m / (kgf-cm/cm)	NB

上列數據仕僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.