



Jacobson van den Berg (Hong Kong) Ltd.

8/E, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408

Polyplastics

SPECIAL LUBRICANT GRADE POM DURACON NW02

性能 Properties	ASTM 測驗方法 ASTM Standards	測試條件 Conditions	單位 Units	DURACON NW02
物理性能 Physical Properties				
比重 Specific Gravity	D792	-	-	1.36
熱性能 Thermal Properties				
熱變形溫度 Heat Deflection Temperature	D648	1.82 Mpa	°C	117
燃燒性 Flammability	UL94	-	-	HB (0.83mm)
機械性能 Mechanical Properties				
拉伸強度 Tensile Strength	D638	-	MPa	52
拉伸長度 Tensile Elongation	D638	-	%	35
撓曲強度 Flexural Strength	D790	-	MPa	77
彎曲模量 Flexural Modulus	D790	-	MPa	2,300
艾佐德衝擊值 Izod Impact Strength	D256	notch side, (Notched 缺口)	J/m	58
		reversed side, (Notched 缺口)		880

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.