



Jacobson van den Berg (Hong Kong) Ltd.

8/F., Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408



離子鍵聚合物
IONOMER RESINS
產品應用：化妝品磨砂容器
SURLYN PC-350

性能 Properties	測驗方法 Test Standards	單位 Units	SURLYN PC-350
物理性能 Physical Properties			
比重 Specific Gravity	ISO R-1183 ASTM D-792	g/cm ³	0.96
熔融流動率 Melt Flow Index (190°C/2.16 kg)	ISO 1133 ASTM D-1238	g/10min	4.5
熱性能 Thermal Properties			
軟化點 Vicat Softening Point	ISO R-306 ASTM D-1525	°C	71
熔化溫度 Melting Temperature	ISO 3146 ASTM D3417	°C	88

上列數據僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.