



Jacobson van den Berg (Hong Kong) Ltd.

8/F, Hong Kong Spinners Ind. Bldg., Phase 6, 481-483 Castle Peak Road, Kowloon, Hong Kong
香港九龍青山道481-483號 Tel : (852) 2828 9328
香港紗廠工業大廈第六期8樓 Fax: (852) 2828 9408

透明及防 UV 級 TRANSPARENCY & UV GRADE ABS SHINKO-LAC U400

性能 Properties		測驗方法 Test Method	單位 Units	SHINKO-LAC U400
物理性質 Physical Properties				
比重 Specific Gravity		ASTM D792	-	1.15
熔融指數 Melt Flow Index	200°C, 5kg	ASTM D1238	g/10min	0.35
洛氏硬度 Rockwell Hardness		ASTM D785	-	R-113
機械性能 Mechanical Properties				
抗拉強度 Tensile Strength		ASTM D638	kg/cm ²	440
彎曲強度 Flexural Strength		ASTM D790	kg/cm ²	530
彎曲模量 Flexural Modulus		ASTM D790	kg/cm ²	20,000
IZOD 衝擊強度 IZOD Impact Strength		ASTM D256	kg-cm/cm	11
熱性質 Thermal Properties				
熱變形溫度 Heat Deflection Temperature		ASTM D648	°C	83
軟化溫度 Vicat Softening Temperature		ISO R-308	°C	94
光學性質 Optical Properties				
透光率 Light Transmittance		ASTM D792	%	92

上列數據仕僅供參考，並不為此承擔任何責任和保證。

The data are intended as a general guide only, makes no guarantee of results and assumes no obligation or liability.